



Technical Datasheet Standard Ion Exchange Membranes

Typical Membrane Characteristics

<i>Membrane type</i>	<i>Anion PC - SA</i>	<i>Anion PC - SA / HD</i>
Width / mm	up to 500	up to 450
Length / mm	up to 1000	up to 1050
Thickness / μm	90 - 130	310 - 350
Ion exchange capacity weak / $\text{meq}\cdot\text{g}^{-1}$ strong / $\text{meq}\cdot\text{g}^{-1}$	ca 0.4 ca 1.1	ca 0.4 ca 1.1
Area resistance		
Temperature Stability, max / $^{\circ}\text{C}$	60	60
Chemical Stability (pH range)	0 - 9	0 - 9
Burst Strength / bar	4 - 5	ca 10
Permselectivity 0.1 m KCl / 0.5 m KCl	> 0.93	> 0.93
Ionic form as shipped	Cl^{-}	Cl^{-}

Membrane Handling

Membranes are delivered wet. They must be kept wet and should be immersed in a solution that is typical in composition to the liquid contacting the membrane in the system prior to assembling the stack.

PCA GmbH
Technical Marketing
Lebacher Strasse 60
D-66265 Heusweiler

Tel: ++49 6806 603732
Fax: ++49 6806 603731
e-mail: info@pca-gmbh.com
www.pca-gmbh.com